



Epoxy-Tie® SET Adhesive - Rebar Yield and Tensile Strength Embedments

Tests have been performed to establish load capacities for rebar dowels installed at multiple embedment depths with Epoxy-Tie SET adhesive. Using these results, the embedment depths required to develop the yield or tensile strengths of Grade 60 rebar have been calculated and are presented below.

Tension Loads and Development Lengths for Rebar Dowels in Normal-Weight Concrete

Rebar Size No. (mm)	Drill Bit Dia. in.	Embed. Depth in. (mm)	f'c ≥ 2000 psi (13.8 MPa) Concrete			f'c ≥ 4000 psi (27.6 MPa) Concrete			ASTM A615 Grade 60 Rebar	
			Ultimate Bond Strength lbs. (kN)	Embed. To Develop Yield Strength in. (mm)	Embed. To Develop Tensile Strength in. (mm)	Ultimate Bond Strength lbs. (kN)	Embed. To Develop Yield Strength in. (mm)	Embed. To Develop Tensile Strength in. (mm)	Yield Strength lbs. (kN)	Tensile Strength lbs. (kN)
#4 (12.7)	5/8	4 1/4 (108)	16,480 (73.3)	4 1/4 (108)	5 1/4 (133)	18,320 (81.5)	4 1/4 (108)	4 1/4 (108)	12,000 (53.4)	18,000 (80.1)
		6 (152)	19,360 (86.1)			19,360 (86.1)				
#5 (15.9)	3/4	5 (127)	24,600 (109)	5 (127)	5 3/4 (146)	26,040 (116)	5 (127)	5 1/2 (140)	18,600 (82.7)	27,900 (124)
		9 3/8 (238)	48,380 (215)			48,380 (215)				
#6 (19.1)	7/8	6 3/4 (171)	38,380 (171)	6 3/4 (171)	7 (178)	40,500 (180)	6 3/4 (171)	6 3/4 (171)	26,400 (117)	39,600 (176)
		11 1/4 (286)	65,020 (289)			65,020 (289)				
#7 (22.2)	1	7 3/4 (197)	47,760 (212)	7 3/4 (197)	8 3/4 (222)	47,760 (212)	7 3/4 (197)	8 3/4 (222)	36,000 (160)	54,000 (240)
		13 1/8 (333)	81,560 (363)			81,560 (363)				
#8 (25.4)	1 1/8	9 (229)	53,680 (239)	9 (229)	11 3/4 (298)	53,680 (239)	9 (229)	11 3/4 (298)	47,400 (211)	71,100 (316)
		15 (381)	94,240 (419)			94,240 (419)				
#9 (28.6)	1 1/4	10 1/8 (257)	53,680 (239)	11 (279)	14 1/2 (368)	53,680 (239)	11 (279)	14 1/2 (368)	60,000 (267)	90,000 (400)
		16 7/8 (429)	111,460 (496)			111,460 (496)				
#10 (31.8)	1 1/2	11 1/4 (286)	76,000 (338)	11 1/2 (292)	17 1/4 (438)	76,000 (338)	11 1/2 (292)	17 1/4 (438)	76,200 (339)	114,300 (509)
		18 3/4 (476)	125,840 (560)			125,840 (560)				
#11 (34.9)	1 5/8	12 3/8 (314)	87,500 (389)	13 3/4 (349)	—	87,500 (389)	13 3/4 (349)	—	93,600 (416)	140,400 (625)
		20 5/8 (524)	132,080 (588)			132,080 (588)				

- Development lengths are based on comparison of average ultimate bond strengths from testing in unreinforced concrete to minimum yield and tensile strengths of rebar.
- Critical edge distance is 1.5 times embedment depth and critical spacing is 4 times embedment depth for unreinforced concrete. Refer to C-SAS-2008 for load adjustment factors for lesser spacings and edge distances. Critical edge distance and critical spacing may be reduced when anchoring into reinforced concrete members.
- Refer to catalog C-SAS-2008 for load adjustment factors for in-service temperature.
- Development lengths may be interpolated for concrete compressive strengths between 2,000 psi and 4,000 psi.
- Anchors are not permitted to support fire-resistive construction. Where not otherwise prohibited by code, anchors are permitted for installation in fire-resistive construction provided that at least one of the following conditions is fulfilled: a) Anchors are used to resist wind or seismic forces only. b) Anchors that support gravity load-bearing structural elements are within a fire-resistive envelope or a fire-resistive membrane, are protected by approved fire-resistive materials, or have been evaluated for resistance to fire exposure in accordance with recognized standards. c) Anchors are used to support nonstructural elements.

This technical bulletin is effective until June 30, 2010, and reflects information available as of April 1, 2008. This information is updated periodically and should not be relied upon after June 30, 2010; contact Simpson Strong-Tie for current information and limited warranty or see www.simpsonanchors.com.

Home Office
5956 W. Las Positas Blvd.
Pleasanton, CA 94588
FAX: 925/847-1603

Southwest U.S.A.
260 N. Palm Street
Brea, CA 92821
FAX: 714/871-9167

Southeast U.S.A.
2221 Country Lane
McKinney, TX 75069
FAX: 972/542-5379

Western Canada
11476 Kingston St.
Maple Ridge, BC V2X 0Y5
FAX: 604/465-0297

Northwest U.S.A.
5151 S. Airport Way
Stockton, CA 95206
FAX: 209/234-3868

Northeast U.S.A.
2600 International Street
Columbus, OH 43228
FAX: 614/876-0636

Eastern Canada
5 Kenview Blvd.
Brampton, ON L6T 5G5
FAX: 905/458-7274

Warehouses & Manufacturing:
Eagan, MN; Enfield, CT; Gallatin, TN;
High Point, NC; Jacksonville, FL; Jessup, MD;
Kent, WA; Langley, BC; Ontario, CA

800-999-5099
www.simpsonanchors.com

© 2008 Simpson Strong-Tie Company Inc.

Printed in the U.S.A.

T-SAS-SETREBR08 4/08 exp. 6/10